


Product Data Sheet



Chinese Blue Limestone



Description

Appearance blue/grey limestone sedimentary rock
Finishes Flamed, Bush Hammered, Sand Blast, Honed, or Polished.
Governing Standards BS EN 1341/1342/1343
Quarry of Origin Shandong P.R.C

Physical Properties

Work Dimensions To customers' specification
Tolerances on Dimensions Class 2
Compressive Strength 131.5 MPa
Flexural Strength 19.5 MPa
Material Density 2730kg/m3 (typically)
Slip Resistance 61 Wet – TLR
75 Dry – TLR
Abrasion Resistance 23.5mm
Water Absorption 0.07%

Supply

Crate Size Maximum 1.8 tonnes. Approx. size 1.0 x 1.0 x 0.80 high
Packaging Wooden crates, suitable for stacking and transportation by fork lift.

Cleaning and Maintenance

Use of mechanical cleaning, especially wire brushing, should be avoided as this will reduce, over time, skid resistance. Washing with clean water should be adequate but not pressure jetting as this could eventually remove the jointing material.

BBS Granite Concepts Ltd
Kimcote House, Walton Road,
Kimcote, Leicestershire
LE17 5RU
Tel: 01455 559474
Email: sales@bbsgraniteconcepts.com
www.bbsnaturalstone.com



BBS Brick & Stone Ltd
Lower Wharfe House,
Wharfebank Mills, Otley, Yorkshire
LS21 3JP
Tel: 01924 241 100
Email: sales@bbsgraniteconcepts.com
www.bbsnaturalstone.com