

# Product Data Sheet



## Oyster Granite



Bush Hammered



Flamed

### Description

Appearance	Medium to coarse grained crystalline rock
Finishes	Flamed, Fine Picked, Cropped, Honed or Polished.
Governing Standards	BS EN 1341/1342/1343 : 2001
Quarry of Origin	Shandong P.R.C

### Physical Properties

Work Dimensions	To customers' specification
Tolerances on Dimensions	Class 2
Compressive Strength	150 MPa
Flexural Strength	17 MPa
Material Density	2630kg/m <sup>3</sup> (typically)
Slip Resistance	64 Wet – TLR 73 Dry – TLR
Water Absorption	0.31%

### Supply

Crate Size	Maximum 1.8 tonnes. Approx. size 1.0 x 1.0 x 0.80 high
Packaging	Wooden crates, suitable for stacking and transportation by fork lift.

### Cleaning and Maintenance

Use of mechanical cleaning, especially wire brushing, should be avoided as this will reduce, over time, skid resistance. Washing with clean water should be adequate but not pressure jetting as this could eventually remove the jointing material.

**BBS Granite Concepts Ltd**  
Kimcote House, Walton Road,  
Kimcote, Leicestershire  
LE17 5RU  
Tel: 01455 559474  
Email: [sales@bbsgraniteconcepts.com](mailto:sales@bbsgraniteconcepts.com)  
[www.bbsnaturalstone.com](http://www.bbsnaturalstone.com)



**BBS Brick & Stone Ltd**  
Lower Wharfe House,  
Wharfebank Mills, Otley, Yorkshire  
LS21 3JP  
Tel: 01924 241 100  
Email: [sales@bbsgraniteconcepts.com](mailto:sales@bbsgraniteconcepts.com)  
[www.bbsnaturalstone.com](http://www.bbsnaturalstone.com)