

Product Data Sheet



Ribbon Granite



Description

Appearance	Medium to coarse grained crystalline rock.
Finishes	Flamed, Fine Picked, Honed, or Polished.
Governing Standards	BS EN 1341/1342/1343:2001
Quarry of Origin	Shandong P.R.C

Physical Properties

Work Dimensions	To customers' specification
Tolerances on Dimensions	Class 2
Compressive Strength	225 MPa
Flexural Strength	21 MPa
Material Density	2660kg/m3 (typically)
Slip Resistance	50 Wet – TLR 68 Dry – TLR
Abrasion Resistance	17.10mm
Water Absorption	0.09%

Supply

Crate Size	Maximum 1.8 tonnes. Approx. size 1.0 x 1.0 x 0.80 high
Packaging	Wooden crates, suitable for stacking and transportation by fork lift.

Cleaning and Maintenance

Use of mechanical cleaning, especially wire brushing, should be avoided as this will reduce, over time, skid resistance. Washing with clean water should be adequate but not pressure jetting as this could eventually remove the jointing material.

BBS Granite Concepts Ltd
Kimcote House, Walton Road,
Kimcote, Leicestershire
LE17 5RU
Tel: 01455 559474
Email: sales@bbsgraniteconcepts.com
www.bbsnaturalstone.com



BBS Brick & Stone Ltd
Lower Wharfe House,
Wharfebank Mills, Otley, Yorkshire
LS21 3JP
Tel: 01924 241 100
Email: sales@bbsgraniteconcepts.com
www.bbsnaturalstone.com