

Product Data Sheet

Vila Amarelo Granite



Description

Appearance
Finishes
Governing Standards
Quarry of Origin

Medium to coarse grained crystalline rock
Flamed, Bush Hammered, Cropped, Honed or Polished.
BS EN 1343:2001.
Vila Real, Portugal

Physical Properties

Work Dimensions To customers' specification
Tolerances on Dimensions Class 2
Compressive Strength 92 MPa
Flexural Strength 14.4 MPa
Material Density 2600kg/m³ (typically)
Slip Resistance 55 Wet – TLR Slider Test
68 Dry – TLR Slider Test
Abrasion Resistance 20.2 mm
Water Absorption 0.40%

Supply

Crate Size Maximum 1.8 tonnes. Approx. size 1.0 x 1.0 x 0.80 high
Packaging Wooden crates, suitable for stacking and transportation by fork lift.

Cleaning and Maintenance

Use of mechanical cleaning, especially wire brushing, should be avoided as this will reduce, over time, skid resistance. Washing with clean water should be adequate but not pressure jetting as this could eventually remove the jointing material.