



Split Face




Morrisons Store, Wetherby



Ashlar Walling



Private House, East Yorkshire



Tumbled



Taylor Wimpey Homes, Boston Spa

Technical Information (typical)

Description	Fine grained limestone	Density	2114 Kg/m ³
Colour	Creamy buff to pink	Compressive Strength	20.7 MPa
Quarry	Hampole Quarry South Yorkshire	Water Absorption	8.5%

Northern Office

Wharfe House, Wharfebank Mills, Ilkley Road
Otley, West Yorkshire, LS21 3JP
Telephone: 01924 241100

Midlands and Southern Office

Kimcote House, Kimcote Court, Walton Road
Kimcote, Leicestershire, LE17 5RU
Telephone: 01455 559474