



Pitched Face



Pitched Face



Ashlar Walling



Ashlar Walling



Pitched Face

Technical Information (typical)

Description	Yorkshire Gritstone	Density	2640 Kg/m ³
Colour	Buff with orange veining	Compressive Strength	47.5 MPa
Quarry	Quarried near Leeds, West Yorkshire.	Water Absorption	3.6%

Northern Office

Wharfe House, Wharfebank Mills, Ilkley Road
Otley, West Yorkshire, LS21 3JP
Telephone: 01924 241100

Midlands and Southern Office

Kimcote House, Kimcote Court, Walton Road
Kimcote, Leicestershire, LE17 5RU
Telephone: 01455 559474