



140mm Split-Faced Walling



140mm Pitched-Faced Walling



Random Cropped & Tumbled



Architectural Masonry



215mm Split-Faced



Random Cropped & Tumbled Reclaimed Mixture



Sawn Paving

Technical Information (typical)

Description	This Yorkshire sandstone has been extensively used for many years, from large prestigious projects such as Jervaulx Abbey and the regeneration of Gateshead town centre, through to residential and commercial projects of all sizes.	Crushing Strength	51.3 MN/m ³
	Colour	Primarily buff with some shade variances and occasional veining	Geographical Type
Mass Density			2201kg/m ³
Acid Immersion Test			Passed
Water Absorption			5.20%
Texture			Fine / Medium Grain

Northern Office

Wharfe House, Wharfebank Mills, Ilkley Road
 Otley, West Yorkshire, LS21 3JP
 Telephone: 01924 241100

Midlands and Southern Office

Kimcote House, Kimcote Court, Walton Road
 Kimcote, Leicestershire, LE17 5RU
 Telephone: 01455 559474